

|  |                      |                          |              |              |   |
|--|----------------------|--------------------------|--------------|--------------|---|
| <b>K-Standard</b>  |                      | <b>20622.0002</b>        |              |              |  |
| Issued by<br>TLL   | Authorized by<br>MAO | Valid from<br>2017-02-20 | Page<br>1(1) | Edition<br>1 |   |
| <b>Oorganisk ytbehandling – tillverkningskrav: Nitrotec®</b>               |                      |                          |              |              |   |
| <b>Inorganic surface treatment – manufacturing requirements: Nitrotec®</b> |                      |                          |              |              |   |

## 1 TILLVERKNINGSKRAV

Processen för värmebehandlingen skall innehålla följande steg:

Tvättning i lösningsmedel och vatten  
Nitrokarburering  
Efteroxidering  
Verifiering

### 1.1 Utseende

Svart halv-matt utseende.

### 1.2 Yta

Följande ytbehandlingsfel tillåts ej:

- frätgropar
- skrovliga skiktytor
- sprickor
- flammiga ytor
- obelagda områden
- flagor

### 1.3 Vidhäftning

Beläggningens vidhäftning ska vara god och får inte visa benägenhet att lossna eller flaga.

### 1.4 Skiktjocklek

Minsta tillåtna skiktjocklek (föreningszon) är 18 µm dvs 6 µm utanpå nominellt mått före ytbehandling .

### 1.5 Korrosionsbeständighet

Korrosionsbeständigheten ska testas enligt K 20982.0001 Accelererande korrosionsprovning.

Tid till basmetallkorrosion : 1,5 vecka

Alternativt,  
ISO 9227 Saltdimsprovning

Tid till basmetallkorrosion: 200 timmar

## 2 METOD

Se K-standard 20622.0001

## 1 MANUFACTURING REQUIREMENTS

The surface treatment shall comprise the following steps:

Washing in solvent and water  
Nitrocarburizing  
By oxidizing  
Verification

### 1.1 Appearance

Black semi-matt appearance.

### 1.2 Surface

The following surface treatment defects are not permitted:

- erosion craters
- rough surfaces
- cracks
- blotchy surfaces
- bare base metal areas
- flakes

### 1.3 Adhesion

The adhesion of the treatment shall be good and may not show susceptibility to get loose or flake.

### 1.4 Coating thickness

Minimum permitted coating thickness (compound layer) is 18 µm i.e. 6 µm outside nominal measure on the part before surface treatment.

### 1.5 Corrosion resistance

The corrosion resistance should be tested according to K-20982.0001 Accelerated corrosion test.

Time until base metal corrosion appears : 1,5 week

Alternatively,  
ISO 9227 Salt spray tests

Time until base metal corrosion appears: 200 hours

## 2 METHOD

Se K-standard 20622.0001